

MBG-C

EnCore® Combined Materials/Mechanically-Bonded Graphite

Description

MBG-C is a high performance gasket material combining graphite facings on a 0.2mm (0.008") tang perforated tin-plated steel core. It is ideally suited for internal combustion engine applications such as head gaskets and exhaust flange gaskets. MBG is compressible and resilient, yet offers excellent bolt torque retention, excellent chemical resistance, and is heat resistant for exhaust gas sealing applications up to 550°C (1000°F) or higher when shielded. The typical values below were established using an overall thickness of 1.2mm (0.047").

Typical Properties

Property	Value	Method
Density, g/cc(lb/cu.ft)	1.00 (62.4) (facings only)	ASTM F 1315
Compressibility, % (at 34.5MPa)	30 - 37	ASTM F 36
Recovery, %	16 - 22	ASTM F 36
Tensile Strength, AMD, MPa(psi)	41.4 (6000)	ASTM F 152
Creep Relaxation, %	4 - 12	ASTM F 38
Fluid Resistance, IRM903 Oil		ASTM F 146
Change in Thickness, %	4 - 13	
Change in Weight, %	18 - 22	
Fluid Resistance, Fuel B		ASTM F 146
Change in Thickness, %	1 - 5	
Change in Weight, %	12 - 16	

Remarks and Related Documents

Typical values determined by the test methods required for ASTM F-104, Type 7 materials.

Interface Performance Materials®, EnCore®, Hydro-Fused®, MicroPore®, Pro-Formance®, Select-a-Seal®, Synthesel®, Thermo-Tork®, and Voltoid® are registered trademarks of Lydall Performance Materials (US), Inc.

WARNING: The performance data provided herein represent typical values. This data sheet is not intended to be used as a purchase specification and does not imply suitability for use in a specific application. Your specific application should not be undertaken without independent study and evaluation for suitability. Failure to select proper sealing products may result in either property damage or personal injury. For specific application recommendations, contact Lydall Performance Materials (US), Inc. (LPM). LPM EXPRESSLY DISCLAIMS ALL WARRANTIES EITHER EXPRESS OR IMPLIED, INCLUDING ANY IMPLIED WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. IN NO EVENT WILL LPM BE LIABLE FOR ANY INDIRECT, SPECIAL, INCIDENTAL, CONSEQUENTIAL OR PUNITIVE DAMAGES, HOWEVER CAUSED AND ON ANY THEORY OF LIABILITY, WHETHER IN CONTRACT, STRICT LIABILITY, OR TORT (INCLUDING NEGLIGENCE OR OTHERWISE) ARISING IN ANY WAY OUT OF THE USE OF THE INFORMATION CONTAINED IN ITS SPECIFICATION DATA SHEETS, ITS PRODUCTS OR THEIR FUTURE USE BY YOU OR ANY THIRD PARTIES, EVEN IF ADVISED OF THE POSSIBILITY OF SUCH DAMAGE.

For more information, please visit www.InterfaceMaterials.com or contact

TECHNICAL CENTER
Lydall Performance Materials (US), Inc.
215 Wohlsen Way
Lancaster, PA 17603
USA
+1.717.207.6000

NORTH AMERICAN SALES OFFICE
Lydall Performance Materials (US), Inc.
22260 Haggerty Road, Suite 200
Northville, MI 48167
USA
+1.248.596.2880

ASIA PACIFIC
Interface Sealing Solutions Shanghai Co., LTD
Unit 14F, No. 728
Yan An Road West, Changning District
Shanghai 200050
China
+8621.5238.5650

INDIA
Lydall Performance Materials India LLP
Mandkola Road, Vill. Atta, Sohna,
Distt. Mewat, Nuh-122103 (Haryana)
+91 8930992166

GERMANY
Lydall Performance Materials Altenkirchen
GmbH
Koblenzer Straße
57610 Altenkirchen
Germany
+49 26818002-0

EUROPE
Lydall Performance Materials Europe
Maison Lili Pean
64240 Bonloc
France
+33 (0) 5.59.29.12.20