

# MP-2N

## Pro-Formance®/MicroPore® Nonasbestos Gasket Material

F729000M9

### Description

MP-2N is specifically engineered for automotive powertrain, marine and small engine applications. It provides exceptional sealability for coolant, lubrication, and induction systems. It conforms well to irregular flange surfaces and is intended for applications with short duration maximum temperatures up to 205°C (400°F).

### Specification Properties

<u>Property</u>	<u>Value</u>	<u>Method</u>
Density, g/cc(lb/cu.ft)	1.35 (84) (min.)	ASTM F 1315
Compressibility, % (at 34.5MPa)	13 - 25	ASTM F 36
Recovery, %	35 (min.)	ASTM F 36
Tensile Strength, AMD, MPa(psi)	8.28 (1200) (min.)	ASTM F 152
Binder Type	Nitrile Butadiene	

### Remarks and Related Documents

Specification values determined by the test methods required for ASTM F-104, Type 7 materials.

Interface Performance Materials®, EnCore®, Hydro-Fused®, MicroPore®, Pro-Formance®, Select-a-Seal®, Synthesel®, Thermo-Tork®, and Voltoid® are registered trademarks of Lydall Performance Materials (US), Inc.

WARNING: The description and performance data provided herein constitute a material specification for quality control purposes, but do not imply suitability for use in a specific application. Your specific application should not be undertaken without independent study and evaluation for suitability. Failure to select proper sealing products may result in either property damage or personal injury. For specific application recommendations, contact Lydall Performance Materials (US), Inc. (LPM). LPM EXPRESSLY DISCLAIMS ALL WARRANTIES EITHER EXPRESS OR IMPLIED, INCLUDING ANY IMPLIED WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. IN NO EVENT WILL LPM BE LIABLE FOR ANY INDIRECT, SPECIAL, INCIDENTAL, CONSEQUENTIAL OR PUNITIVE DAMAGES, HOWEVER CAUSED AND ON ANY THEORY OF LIABILITY, WHETHER IN CONTRACT, STRICT LIABILITY, OR TORT (INCLUDING NEGLIGENCE OR OTHERWISE) ARISING IN ANY WAY OUT OF THE USE OF THE INFORMATION CONTAINED IN ITS SPECIFICATION DATA SHEETS, ITS PRODUCTS OR THEIR FUTURE USE BY YOU OR ANY THIRD PARTIES, EVEN IF ADVISED OF THE POSSIBILITY OF SUCH DAMAGE.

For more information, please visit [www.InterfaceMaterials.com](http://www.InterfaceMaterials.com) or contact

TECHNICAL CENTER  
Lydall Performance Materials (US), Inc.  
215 Wohlsen Way  
Lancaster, PA 17603  
USA  
AE@InterfaceMaterials.com  
+1.717.207.6000

NORTH AMERICAN SALES OFFICE  
Lydall Performance Materials (US), Inc.  
22260 Haggerty Road, Suite 200  
Northville, MI 48167  
USA  
+1.248.596.2880

ASIA PACIFIC  
Interface Sealing Solutions Shanghai Co., LTD  
Unit 14F, No. 728  
Yan An Road West, Changning District  
Shanghai 200050  
China  
+8621.5238.5650

INDIA  
Lydall Performance Materials India LLP  
Mandkola Road, Vill. Atta, Sohna,  
Distt: Mewat, Nuh-122103 (Haryana)  
+91 8930992166

GERMANY  
Lydall Performance Materials Altenkirchen  
GmbH  
Koblenzer Straße  
57610 Altenkirchen  
Germany  
+49 26818002-0

EUROPE  
Lydall Performance Materials Europe  
Maison Lili Pean  
64240 Bonloc  
France  
+33 (0) 5.59.29.12.20